

SoundBloc™

Gyproc® SoundBloc™ MR Plasterboard

Technical & Safety Datasheet



INTRODUCTION

Characteristics

Gypsum plasterboard with a higher density core and water repellent additives specifically designed to achieve greater levels of sound insulation. Gyproc SoundBloc™ MR consists of an aerated gypsum core encased in, and firmly bonded to, strong paper liners. Gyproc SoundBloc™ MR is a plasterboard that is suitable for drylining internal surfaces.

Applications

Gyproc SoundBloc™ MR is designed for use in Gyproc® partition, lining and ceiling systems where greater levels of sound insulation and moisture resistance are required.

Board colour

- Faced with blue coloured paper
- Reverse faced with green coloured paper

Board printing

Reverse - Standards, date, time and location of manufacture, board dimensions & edge type

Board range

| Width* | Length* | Edge type |
|---------------------|------------|--|
| mm | mm | |
| 12.5mm board | | Kg/m² = 11.5 R (m²K/W) = 0.05 |
| 1200 | 2400, 3000 | Tapered Edge |
| 15mm board | | Kg/m² = 13.6 R (m²K/W) = 0.06 |
| 1200 | 2400, 3000 | Tapered Edge |

* Other lengths & thicknesses available upon request

STANDARDS

EN 520:2004+A1:2009 Gypsum Plasterboards, definitions, requirements and test methods

Type D: Gypsum plasterboard with controlled density
 These boards have a controlled density, with a face to which suitable gypsum plasters or decoration may be applied. This enables improved performance in certain applications to be obtained.

Type H1: Plasterboard with reduced water absorption rate.
 Boards which have additives to reduce the water absorption rate. They may be suitable for special applications in which reduced water absorption properties are required to improve the performance of the board. For the purposes of identification, these boards are designated Type H1, H2 and H3, with different water absorption performance..

ASTM C1396-17 Standard Specification for Gypsum Board

Section 5: Gypsum wallboard, Predecorated Gypsum Board and Laminated Gypsum Board

Section 7: Water-resistant gypsum backing board

Section 12: Gypsum Ceiling Board

BOARD PERFORMANCE

Fire protection

Plasterboard linings provide good fire protection owing to the unique behaviour of the noncombustible gypsum core when subjected to high temperatures.

Fire resistance

Please refer to the appropriate White Book product or systems section for information on the fire resistance of building elements lined with Gyproc SoundBloc™. The substitution of Gyproc SoundBloc™ with the same thickness of Gyproc SoundBloc™ MR will not change the fire performance.

| Standard | Performance |
|--|---|
| BS 476: Part 6: 1989 Method of test for fire propagation for products. | Index of performance (I) not exceeding 12 and a sub-index (i1) not exceeding 6. |
| BS 476: Part 7: 1997 Surface spread of flame tests for materials. | Class 1 (both sides). |
| EN 520:2004+A1:2009 | Classified without further testing as A2-s1, d0. |
| ASTM E84-17a | Class 1/Class A |

Thermal conductivity (λ)

Gyproc SoundBloc™ MR - 0.25W/mK

Effect of temperature

Gyproc SoundBloc™ MR is unsuitable for use in areas subject to continuously damp or humid conditions and must not be used to isolate dampness. Plasterboards are not recommended to be stored in temperature above 49°C for prolonged period but can be subjected to freezing condition without risk of damage.

Effect of condensation

The designers should take care to eliminate all possibility of problems caused by humidity and condensation.

INSTALLATION

General

It is important to observe appropriate health and safety legislation when working on site i.e. personal protective clothing and equipment, etc. The following notes are intended as general guidance only. In practice, consideration must be given to design criteria requiring specific project solutions.

Handling

Manual offloading of this product should be carried out with care to avoid unnecessary strain. For further information please refer to the Manual Handling section of the Middle East WHITE BOOK.

Cutting

This product may be cut using a plasterboard saw or by scoring with a sharp knife and snapping the board over a straight edge. Holes for switch or socket boxes should be cut out before the boards are fixed using a utility saw or sharp knife. When cutting boards, power and hand tools should be used with care and in accordance with the manufacturers' recommendations. Power tools should only be used by people who have been instructed and trained to use them safely. Appropriate personal protective equipment should be used.

Fixing

Fix boards with decorative side out to receive joint treatment or a skim plaster finish. Lightly butt boards together. Never force boards into position. Install fixings not closer than 13mm from cut edges and 10mm from bound edges. Position cut edges to internal angles whenever possible, removing paper burrs with fine sandpaper. Stagger horizontal and vertical board joints between layers by a minimum of 600mm. Locate boards to the centre line of framing where this supports board edges or ends.



FINISHING

Board edge types

T/E - for tapered and filled joints using Gyproc® jointing materials

Jointing

Gyproc® jointing materials produce durable joint reinforcement and a smooth, continuous, crack-resistant surface ready for priming and final decoration. A number of jointing specifications are available to suit the board type, method of application, and site preference.

Decoration

After the joint treatment has dried, decoration, including any decorator's preparatory work, should follow.

Repair

Minor damage - Lightly sand the surface to remove burrs and fill flush with two applications of Gyproc® Jointing Compound. When dry, decoration including any decorator's preparatory work should follow.

Deep indents resulting from impact - Check the plasterboard core to ensure that it is not shattered. If intact, apply a coat of Gyproc® Jointing Compound followed by the procedure for repairing minor damage once set/dry.

Damaged core and/or broken edges (non-fire rated or non-high impact situations only) - Remove the damaged area of core. Score the liner approximately 10mm away from the undamaged core around the damaged area, and peel the paper liner away. Apply PVA to seal the core and surrounding liner. Bulk fill the hole with Gyproc® Jointing Compound and strike off flush. Once the filler is set/dry, follow the procedure for repairing minor damage.

Extensive damage - When the damage is more extensive or the partition is fire rated or has a high impact resistant requirement, it may be necessary to replace that area of plasterboard. It is important that the replacement board is of the same type as specified and installed. Cut out the affected area back to the nearest framing member. Replace the plasterboard, accurately cutting and screw fixing the same type and thickness of plasterboard. Fill edge joints, then tape using Gyproc® Jointing Tapes and finish in the recommended way. When dry, decoration including any decorator's preparatory work should follow.

HEALTH & SAFETY

1. Identification of the substances/ preparation and company

Gyproc SoundBloc™ MR

Supplier Saint-Gobain Gyproc Emirates Industries L.L.C
ICAD 1, Mussafah
Abu Dhabi
United Arab Emirates
P.O. Box 38983

Free Phone: +971 800 GYPROC (497762)

E-Mail: gyproc-me@saint-gobain.com

This information reflects typical values and is not a product specification.

2. Hazards identification

2.1 Classification of the article:

This product is not classified as hazardous according to CHIP.

Dust from sawing or sanding may irritate the respiratory system, skin and eyes.

3. Composition / information on ingredients

General composition: Calcium sulphate dihydrate encased in paper liners, natural constituents may include minor amounts of quartz. Small quantities of chopped glass fibre, microsilica and vermiculite may be added, with starch, foam and dispersants.

Any board may contain small quantities of chopped manmade mineral fibre and microsilica.

4. First aid measures

Eye contact S26 - In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
S39 - Wear eye / face protection.

Skin contact S28 - After contact with skin, wash immediately with plenty of soap and water.
S36 - Wear suitable protective clothing.

Ingestion S62 - If swallowed, do not induce vomiting, seek medical advice immediately and show this document.
S64 - If swallowed, rinse mouth with water (only if the person is conscious).

Inhalation S51 - Only use in well ventilated areas.
S63 - In case of accident by inhalation, remove casualty to fresh air and keep at rest.

General Get medical attention if any symptoms persist.

5. Fire fighting measures

The product does not pose a fire hazard. However, some packaging materials or facings may burn.

Suitable extinguishing media - water, foam, carbon dioxide or dry powder.

6. Accidental release measures

Not applicable.

7. Handling and storage

7.1 Precautions for safe handling:

Use - Minimise dust generation when sawing or sanding in poorly ventilated places. Avoid eye contact - see Section 8 for recommended personal protective equipment, and Section 2 for hazards identification.

Plasterboards will not support body weight in between rafters, joints or frame members.

Manual handling - Sheets of plasterboard can be unwieldy, use an appropriate lifting technique. The weight of each sheet can vary between products. For manual handling purposes assume the following:

Gyproc SoundBloc™ MR weights

| Product | Board thickness mm | Board width mm | Board length mm | Board weight kg | Pallet weight kg |
|----------------------|--------------------|----------------|-----------------|-----------------|------------------|
| Gyproc SoundBloc™ MR | 12.5 | 1200 | 2400 | 33.2 | 1980 |
| | | | 3000 | 41.5 | 1909 |
| | 15 | 1200 | 2400 | 39.2 | 1932 |
| | | | 3000 | 49.0 | 2040 |

NB All weights are approximate.

Mechanical handling - The dimensions of the pallet vary depending on the product size. To avoid potentially overloading a lift truck, it is important that any effect on load centres is considered. The nominal weight of each palletised load is given within the weights table in this section of this document.

7.2 Conditions for safe storage, including any incompatibilities:

Storage - Store on pallets supplied in dry conditions. To maintain stability place pallets on firm level ground and ensure that stacks are both level and vertical.

When working with individual boards, only work from a single pallet, not a stack.

Pallet stacking heights

The maximum stack heights on level concrete on level concrete floors and vertical stacks are as follows:

NB

| Board width mm | Board length mm | Pallet stack height packs |
|----------------|-----------------|---------------------------|
| 1200 | 2400, 3000 | 6 |

HEALTH & SAFETY (CONTINUED)

8. Exposure control / personal protection

Workplace exposure limit

| Substance | Total inhalable | Respirable |
|---------------------------------|---|------------------------------|
| Plaster | 10mg/m ³ 8hr TWA | 4mg/m ³ 3hr TWA |
| Quartz (silica) | - | 0.1mg/m ³ 8hr TWA |
| Man Made Mineral Fibres (MMMMF) | 5mg/m ³ 8hr TWA (gravimetric method) | - |

Personal protection

Respiratory S51 - Use only in well ventilated areas.
S39 - Wear eye / face protection.
Face masks to EN 149 FFP2.

Skin S36 - Wear suitable protective clothing.

Eye S39 - Wear eye / face protection.
Eye protection to BS EN 166.

9. Physical and chemical properties

Appearance Flat sheet boards with a tapered edge.

10. Stability and reactivity

No special physical conditions need to be avoided. No specific restrictions regarding incompatible materials.

11. Toxicology information

No known toxicological effects.

12. Ecological information

Stable product with no known adverse environmental effects.

13. Disposal consideration

Waste from gypsum plasterboard products is normally classified as 'non-hazardous, non-inert', is fully recyclable and is classified as EWC 02 08 17.

If you would like to recycle Gypsum plasterboard waste, we at Gyproc offer Gypsum recycling services and are happy to take segregated waste from your site.



Please refer to the Gyproc® Plasterboard Recycling brochure.

Always seek advice of a trained and competent professional. Off-cuts, where appropriate, can be used as noggings to reduce or remove recycling requirement.

Alternatively, Plasterboard waste can be disposed off at an authorized landfill site in accordance with the local waste management regulations.

14. Transport information

Not classified as hazardous for transportation.

15. Regulatory information

Not classified under the CHIP regulations.

16. Other information

Control of Substances Hazardous to Health Regulations (COSHH)
The Manual Handling Operations Regulations
HSE Guidance Note EH40: Workplace Exposure Limits
Gypsum Wastes – Environment Agency Information Sheet
Gyproc Middle East **WHITE BOOK**
Gyproc Middle East website: www.gyproc.ae

Note to user: This Safety Data Sheet does not constitute a workplace risk assessment for COSHH.

There are a number of situations where the approach to manual handling of Gyproc® products should be considered. For further guidance, please refer to the Manual Handling Section of The White Book, available to download from www.gyproc.ae



SpecSure® is a unique 'off the shelf' warranty to end users that confirms Gyproc® proprietary systems will perform to the parameters published in our current literature from the day they are installed.

SpecSure® - a warranty for the future performance of your system.



Saint-Gobain Gyproc Middle East FZE
P.O.Box.261107
Dubai, UAE
Tel: +971 (4) 450 2300
Fax:+971(4) 446 8701

Saint-Gobain Gyproc Emirates Industries LL.C
P.O. Box 38983
ICAD 1, Mussafah
Abu Dhabi, UAE

www.gyproc.ae

First Edition
Literature Code: 0284-DS-001

June 2019

